




NOTES:


- 1. FOR HARDWOOD TIMBER EDGE DETAIL, REFER TO CoA 412
- 2. WHERE "RED OXIDE" OR "OXIDE" COLOURED ASPHALT IS SPECIFIED, THE ASPHALT MIX SHALL BE MADE UP BY SUBSTITUTING 2% (BY WEIGHT) OF THE FINE SAND IN THE STANDARD AC7 MIX WITH ABILOX LIGHT RED 109 OXIDE POWDER, OR APPROVED EQUIVALENT (MEXPHLATE C IS NOT REQUIRED AS A BINDER SUBSTITUTE)





NOTES:

- 1. FOR HARDWOOD TIMBER EDGE DETAIL, REFER TO CoA 412
- 2. WHERE "RED OXIDE" OR "OXIDE" COLOURED ASPHALT IS SPECIFIED, THE ASPHALT MIX SHALL BE MADE UP BY SUBSTITUTING 2% (BY WEIGHT) OF THE FINE SAND IN THE STANDARD AC7 MIX WITH ABILOX LIGHT RED 109 OXIDE POWDER, OR APPROVED EQUIVALENT (MEXPHLATE C IS NOT REQUIRED AS A BINDER SUBSTITUTE)





NOTES:

- . FOR SPECIFIC CONCRETE MIX DETAILS, CONTACT CoA
- 2. PROVIDE LIGHT WASHED EXPOSED AGGREGATE FINISH TO TOP SURFACE
- 3. REPLACE ENTIRE SECTION OF CONCRETE TO EXISTING JOINTS

GENERAL NOTES:

- MATERIALS PROVIDED AND PAVEMENTS CONSTRUCTED IN ACCORDANCE WITH D.I.T. SPECIFICATIONS UNLESS OTHERWISE NOTED
- 2. EXCLUDE LOADING CATEGORIES REFERENCE FROM CoA 420 FOOTPATHS LOADING MAP

REV	DESCRIPTION	DATE
Α	ORIGINAL ISSUE	09/22

CONSTRUCTION STANDARD PAVEMENT

FOOTPATH DETAILS
FOR GENERAL MAINTENANCE / MINOR REINSTATEMENT

